

BITUMEN UNDERBODY PROTECTION SPRAY

Features

- long-term protection against rust and stone chips
- very good adhesion to metallic surfaces
- forms a permanent, visco-elastic and unified protective film with anti-buzzing effect
- resistant to water, salt spray, oil as well as diluted acids and bases
- cannot be re-coated

Areas of application

PETEC bitumen-based underbody protection offers optimum protection against stone chips and rust in corrosive environments with very good adhesion to metallic surfaces. Bitumen underbody protection forms a permanent, visco-elastic and closed protective film with anti-buzzing effect.

TechnicalData

Base	Bitumen
Colours	black
Curing	2 hours at 500 µm
Curing system	Humidity
Shelf life	36 Months
Salt spray test	1,000 at 400 µm (Ri0)
Temperature Resistance	-25 - +100

Usage Instructions

Application temperature: +5°C to +30°C. Shake well before use. Spray PETEC bitumen underbody protection on the rust-free, clean, dry and degreased surface from a distance of approx. 25 cm. For thicker layers, we recommend to let the product dry, before applying the next layer. Check on beforehand if the materials are compatible. Danger of autoxidation on alloys. The product contains solvents which may dissolve or attack existing coatings. Different underbody protection products should therefore not be combined with each other without conducting your own tests first.

Always conduct your own tests to ensure that the product is suitable for each application. Cannot be re-coated. Do not apply on the brake and exhaust system, heat plates or rubber parts. After use, turn the can upside down and spray until the valve is empty. Read the safety and technical data sheet! (Download the PETEC data sheets at www.petec.de)

Package Sizes

		
Item no.: 73100	Item no.: 73110	Item no.: 73150
1000 ml	1000 ml	500 ml