

## **TechDataSheet**

## **2C PU ADHESIVE**

#### **Features**

Fast-curing 2-component adhesive for repairing and bonding plastics.

- · also for bonding and filling holes, cracks and joints in metal, wood, stone, concrete and glass
- · super-fast curing action and fast finishing
- · very strong bond, slightly flexible and resistant to breakage
- · does not drip, easy to mould
- can be ground and re-coated with many paint finishing systems
- resistant to water, salt water, coolant, oil, as well as many chemicals and fuel to some extent

## Areas of application

Area of application: For repairing bumpers, spoilers, radiator grilles, trim clips, brackets (e.g. headlights) and broken plastic parts and trim. Also for bonding and filling holes, cracks and joints in metal, wood, stone, concrete and glass

#### **TechnicalData**

Base	polyurethane
Colours	black
CuringMinutes	20
Curing system	2-C
Elongation at break	170
Hand strength	3
Shelf life	24 Months
ShoreAHardness	65
Temperature Resistance	-40 - +140
Pot life	1
Application temperature	+5 - +30
Tensile Shear Strength	16

## **Usage Instructions**

Application temperature: +5°C to +30°C. Lightly sand the surface, if possible, and thoroughly clean and degrease it with PETEC Multi Cleaner (item no. 82100 / 82200). Sand down V-shaped cracks. We recommend using as an adhesive agent PETEC plastic primer (item no. 98315). Insert the double cartridge into the PETEC applicator gun (item no. 98502) and remove the cap. Squeeze out the required amount and mix or attach a mixing tube (avoid pausing for more than one minute, because the adhesive will harden in the mixing tube). Then, apply immediately to the bonding surface. Join together the materials to be bonded within one minute. After use, close off the double cartridge with the cap. Reworking (e.g. sanding, varnishing) can only be done after the adhesive has cured. Varnishes and other media containing solvents may inhibit or ruin the curing process. In-house testing and suitability testing is required given the numerous applications, materials and other influencing factors. Read the safety and technical data sheet. (Download the PETEC data sheets at www.petec.de)

LiabilityClauseText



# **TechDataSheet**

# **Package Sizes**

PETEC S  PROPERTY S  The second of the secon	PICSTBONG PLITT
Item no.: 98325	Item no.: 98350
24 ml	50 ml

Liability Clause Text