

INOX SPRAY

Features

- weldable surface sealant
- welding and corrosion protective coating
- compatible with many different types of metals
- remarkable covering power
- prevents contact corrosion
- silicone-free
- resistant to water, salt water, as well as weak acids and bases

Areas of application

PETEC INOX Spray is a fast-drying, universal surface coating. The anti-corrosive offers remarkable adhesion properties and permanently seals welding points and seams. The product protects against corrosion when welding two materials. Also suitable for use in inert gas welding (IGW) and spot welding as a welding point sealant. For applications in the sectors body and automotive construction, metal structure, welding, ship construction, construction and agricultural machinery as well as industry and trades.

TechnicalData

Colours	silver
Touch dry	15
Shelf life	36 Months
Dry dust-free	5
Temperature Resistance	+120

Usage Instructions

Application temperature: +5°C to +25°C. Shake can well before use. Remove coarse residues from the surfaces (e.g. from sandblasting or grinding) and then thoroughly clean and degrease with PETEC Multi Cleaner (item no. 82100 or 82200). Spray evenly and crosswise several thin layers of PETEC INOX spray from a distance of approx. 20 cm onto the surface to be coated. Allow the product to dry for about 4 minutes between the spray cycles. Can be welded after approx. 2-3 hours using the appropriate welding technique. The drying time depends on the layer thickness, the ambient temperature and the humidity. The entire drying process takes 24 hours. Coatings should only be applied using suitable products and once the surface has fully cured. Varnishes and other media containing solvents may inhibit or ruin the curing process. Always conduct your own tests to ensure that the product is suitable for each application. After use, turn the can upside down and spray until the valve is empty. Read the safety and technical data sheet. (Download the PETEC data sheets at www.petec.de)

Package Sizes



Item no.: 70360

500 ml

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.