

STONE CHIP & UNDERBODY PROTECTION AQUA

Features

- ecofriendly
- solvent-free
- no streak formation and no dripping
- can be re-coated
- dries visibly, fast further processing
- abrasion-resistant structure, fast drying and sandable
- protects repair and body parts from rust and stone chips
- does not become brittle or cracked and adheres even at high temperatures
- resistant to water, salt spray, oil as well as diluted acids and bases
- restores the OEM structure
- breathable underbody protection, also suitable for wood applications in the caravan sector

Areas of application

PETEC water-based stone chip and underbody protection can be re-coated and provides very good adhesion to many surfaces. For optimum protection against rust and stone chips in many corrosion-prone areas. When dried, stone chip and underbody protection forms an elastic, structural and unified protective film with anti-buzz effect.

TechnicalData

Base	hydrogen mixture
Colours	grey
Working pressure	4 - 6
CuringHours	2 hours at 500 µm
Curing system	Humidity
Shelf life	36 Months
Salt spray test	>1,000 at 400 µm (Ri0)
Temperature Resistance	-30 - +140

Usage Instructions

Application temperature: +5°C to +30°C. Shake can well before use. Spray PETEC stone chip and underbody protection on the rust-free, clean, dry and degreased surface from a distance of approx. 25 cm using the PETEC underbody protection gun (item no. 98507). Can be re-coated after through drying. Varnishes and other media containing solvents may inhibit or ruin the curing process. For thicker layers, we recommend to let the product dry before applying the next layer. Check on beforehand if compatible with the material. Danger of autoxidation in alloys. Always conduct your own tests to ensure that the product is suitable for each application. Do not apply to the brake and exhaust system, heat plate or rubber parts. Clean the underbody protection gun after use. Read the safety and technical data sheet. (Download the PETEC data sheets at www.petec.de)

Package Sizes


Item no.: 73710
1000 ml

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.