TechDataSheet

WINDOW & BODY SEALANT, BLACK

Features

Long-lasting adhesion of windows & body sealants made of butyl rubber for permanent sealing of front, rear, and side windows, body and attached parts.

- · permanent sealing of many materials
- · permanently adhesive, does not harden
- can be dabbed off with itself

- for large-area sealing applications
- balances tensions within the body
- reliably prevents the infiltration of moisture, dirt and draught
- · resistant to water, salt water, as well as diluted acids and alkaline solutions

Areas of application

Can be used for sealing structures, highly-stressed joints and vibrating parts in body and container construction. For applications in the automotive, caravan, marine, construction and agricultural machinery sector, as well as in industry and trade.

TechnicalData

Base	butyl rubber
Colours	black
Shelf life	24 Months
Temperature Resistance	-30 - +80

Usage Instructions

Application temperature: +5°C to +40°C. Thoroughly clean and degrease sealing surfaces with PETEC Multi Cleaner (item no. 82100 or 82200). Cut open the cartridge above the thread, cut the nozzle and screw on. Apply a layer with the desired thickness on one side using an applicator gun, adjust and fix the parts if necessary. Surplus material must be dabbed off with itself after drying. Check on beforehand if the materials are compatible. Always conduct your own tests to ensure that the product is suitable for each application. Read the safety and technical data sheet! (Download the PETEC data sheets at www.petec.de)

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.



TechDataSheet

Package Sizes

Item no.: 83300	ltem no.: 83290
310 ml	310 ml

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.

www.petec.de