

# POWER ADHESIVE BRUSH BOTTLE

## Features

1-component adhesives for long-lasting connections that harden in a matter of seconds.

- super fast adhesion and hardening within a few seconds
- easy to use
- very high strength
- clean bonding
- can be immediately further processed

## Areas of application

Bonds materials such as metal, plastic, rubber, felt, PVC, leather, wood, ceramic and many others - of the same kind or with each other.

## TechnicalData

|                        |                     |
|------------------------|---------------------|
| Base                   | ethyl cyanoacrylate |
| Colours                | clear               |
| Functional stability   | 1-10                |
| Shelf life             | 18 Months           |
| Gap Bridging           | 0.05                |
| Temperature Resistance | -40 - +85           |
| Tensile Shear Strength | 15-25               |

## Usage Instructions

Application temperature: +5°C to +30°C. Thoroughly clean and degrease surfaces with PETEC Multi Cleaner (item no. 82100 or 82200). For low-energy plastics, we recommend using plastic primers (item no. 98315) for promoting the adhesion. Apply POWER adhesive thinly on one side with the brush. Align the parts to be bonded accurately and press them firmly together. The rapid chemical reaction can lead to white residues on the surface. Reworking (e.g. sanding, varnishing) can only be done after the adhesive has cured. Varnishes and other media containing solvents may inhibit or ruin the curing process. For quicker hardening we recommend our SpeedBond activator spray (item no. 93515). Given the numerous applications, materials and other influencing factors in-house testing and suitability testing is required. Read the safety and technical data sheet. (Download the PETEC data sheets at [www.petec.de](http://www.petec.de))

### Package Sizes

|   |
|---|
|  |
| <b>Item no.: 93404</b>  |
| 4 g blister pack  |

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.