

# POWER ADHESIVE, UNIVERSAL & STRONG

## Features

Elastic, 1-component adhesive and sealant with strong initial adhesion and final strength. PETEC power adhesive is suitable for secure, durable and dynamically stressed bonds and sealings.

- broad range of adhesive applications
- strong initial adhesion and final strength
- excellent sealing properties
- high elastic and dynamic load capacity
- silicone-free, solvent-free, isocyanate-free
- resealable tip
- can be re-coated
- resistant to ageing, weatherproof, UV-resistant and water-resistant

## Areas of application

For bonds and seals in body, vehicle and container construction. Applications in the automotive field: e.g. wheel guard, spoiler, mudguard, vehicle underbody, boot floor, seams on the front and rear spoilers, seam sealing. Also for assembly bonds on metal, glass, stone, concrete, plaster, gypsum, tiles, natural stone, wood, varnished surfaces, mirrors, PVC and many plastics.

## TechnicalData

Base	1-C modified silane polymers
Colours	black
Initial adhesion	196
Curing	3
Curing system	Humidity
Elongation at break	300
Shelf life	24 Months
ShoreAHardness	65
Temperature Resistance	-40 - +100
Pot life	20
Application temperature	+5 - +40
Consumption	25
Tensile Shear Strength	1.4

## Usage Instructions

Application temperature: +5°C to +40°C. Thoroughly clean and degrease adhesive and sealing surfaces with PETEC Multi Cleaner (item no. 82100 or 82200). Using the PETEC applicator gun (item no. 81500), apply the desired coat thickness on one side in the form of beads, align the parts and press firmly. Coatings should only be applied using suitable products and once the surface has fully cured. Varnishes and other media containing solvents may inhibit or ruin the curing process. Always conduct your own tests to ensure that the product is suitable for each application. Read the safety and technical data sheet! (Download the PETEC data sheets at [www.petec.de](http://www.petec.de))

### Package Sizes



**Item no.: 94229**

290 ml cartridge

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.