

# LIQUID METAL

## Features

2-component epoxy resin metal for filling, smoothing and bonding.

- excellent adhesion to all metals, such as iron, steel, cast, aluminium, alloys and many more, as well as ceramic, concrete, wood and many plastics
- rapid curing
- high strength and excellent adhesion to other kinds of material
- can be machined, sanded and re-coated with many paint finishing systems
- resistant to water, salt water, coolant, oil, as well as many chemicals and fuel to some extent

## Areas of application

Suitable for repairing iron, steel, cast, ceramic, concrete, wood and many plastics. Suitable for filling, smoothing and bonding of rips, holes, drilling mistakes, cavities. For repairing pipes, tanks, threads, body and machine parts.



## TechnicalData

Base	epoxy resin
Colours	grey
CuringMinutes	30
Curing system	2-C
Hand strength	10
Shelf life	12 Months
Temperature Resistance	-30 - +120
Pot life	4
Tensile Shear Strength	25

## Usage Instructions

Application temperature: +5°C to +60°C. Lightly sand the surface if possible and thoroughly clean and degrease it with PETEC Multi Cleaner (item no. 82100 or 82200). Remove the cap, squeeze out the required amount, mix (avoid pausing for more than four minutes) and apply directly to the site to be repaired. Join together the materials to be bonded within four minutes. After use, replace the cap on the double syringe. Reworking (e.g. sanding, varnishing) can only be done after the adhesive has cured. Varnishes and other media containing solvents may inhibit or ruin the curing process. In-house testing and suitability testing is required given the numerous applications, materials and other influencing factors. Please do not use a mixing tube with the liquid metal 25 ml double syringe! Read the safety and technical data sheet. (Download the PETEC data sheets at [www.petec.de](http://www.petec.de))

### Package Sizes

	
<p><b>Item no.: 97425</b></p>	<p><b>Item no.: 97355</b></p>
<p>25 ml without mixing tube</p>	<p>50 ml</p>

Our technical application advice, whether verbal, in writing, or based on tests, is provided to the best of our current knowledge. However, it does not release you from the obligation to independently verify the suitability of the products we supply for the intended processes and purposes. The application, use, and processing of the products are beyond our control and therefore fall solely within your area of responsibility.